

Data Sheet Compri-pol/J

<u>density</u>	30	kg/m ³	ISO 845
<u>temperature range</u>	-30 to +80	°C	
<u>elongation at break</u>	lengthwise 125 crosswide 115	%	ISO 1926 ISO 1926
<u>compressive strength</u> at 50% compression	98	kPa	ISO 844
<u>compression set</u> 25%/22 h, 23°C	20 (0,5h after discharge) 12 (24h after discharge)	%	ISO 1856-B ISO 1856-B
<u>peel adhesion</u>	material break		DIN EN 1939
<u>tensile strength</u>	lengthwise 325 crosswide 220	kPa	ISO 1926 ISO 1926
<u>adhesive</u>	synthetic rubber hot-melt		
<u>release liner</u>	siliconized PE-foil		
<u>resistance to high humidity</u>	very good		
<u>water absorption (7d)</u>	<1	Vol.-%	

This information only relate to the rubber foam material and not to the adhesive or the adhesive property.
All mentioned data are guideline values, a commitment cannot be deducted.